

# 24 LMD LOT 8170 GOTS



## KARTA TECHNICZNA / TECHNICAL DATASHEET

CREATION DATE: **06.12.2021**

- 100% FLAX YARN     DRY-SPUN     FLAX ROVING     SINGLE  
 100% HEMP YARN     WET-SPUN     FLAX LOW TWIST YARN     TWIST  
 BLEND:     FLAX / PA  
                    FLAX / HEMP

Nm **24**  
TEX **42**

TYPE **LMD**

LOT **8170**  
DIAMETER **205**  
PARAFFINE **NO**

PARAMETER	Nm real	Force avg [N]	CV force [%]	Elongation avg [%]	Elongation min [%]	RKM min	RKM 3 points min	RKM max	RKM avg	Um [%]	CVm [%]	Points m (-50%)	Points g (+50%)	Points g (+100%)	Points g (+200%)	Points g (+400%)	Whiteness % CIE
X	<b>23,63</b>	<b>14,55</b>	<b>15,46</b>	<b>2,11</b>	<b>1,47</b>	<b>21,44</b>	<b>23,19</b>	<b>50,05</b>	<b>35,05</b>	<b>21,34</b>	<b>27,63</b>	<b>2 020</b>	<b>1 091</b>	<b>74</b>	<b>4 771</b>	<b>515</b>	<b>44,42</b>
SD	0,29	0,64	1,30	0,11	0,20	2,96	2,49	1,72	1,50	0,31	0,43	206	60	11	394	55	1,84
CV	1,23	4,41	8,42	4,97	13,94	13,80	10,75	3,44	4,27	1,43	1,56	10	6	15	8	11	4,13
min	23,35	13,91	13,58	1,98	1,21	17,44	19,24	47,16	33,40	20,74	27,04	1 571	1 008	63	4 077	426	40,69
max	24,14	15,84	17,64	2,28	1,76	25,61	26,04	51,79	37,70	21,64	28,19	2 227	1 191	95	5 358	586	46,78

No of tested cones **32**