

24 LML LOT 8219



KARTA TECHNICZNA / TECHNICAL DATASHEET

CREATION DATE: **07.12.2021**

- 100% FLAX YARN DRY-SPUN FLAX ROVING SINGLE
 100% HEMP YARN WET-SPUN FLAX LOW TWIST YARN TWIST
 BLEND: FLAX / PA
 FLAX / HEMP

Nm **24**
TEX **42**

TYPE **LML**

LOT **8219**
DIAMETER **205**
PARAFFINE **NO**

PARAMETER	Nm real	Force avg [N]	CV force [%]	Elongation avg [%]	Elongation min [%]	RKM min	RKM 3 points min	RKM max	RKM avg	Um [%]	CVm [%]	Points m (-50%)	Points g (+50%)	Points g (+100%)	Points g (+200%)	Points g (+400%)
X	24,05	13,36	15,11	1,94	1,33	20,45	22,89	45,39	32,78	20,93	26,86	1 839	940	49	2 679	201
SD	0,33	0,54	1,16	0,07	0,13	2,09	0,96	3,41	1,50	0,30	0,37	180	59	6	380	28
CV	1,37	4,03	7,66	3,40	9,83	10,20	4,18	7,50	4,58	1,44	1,39	10	6	13	14	14
min	23,72	12,49	13,67	1,85	1,09	16,68	21,50	41,50	30,23	20,60	26,47	1 680	860	36	2 188	158
max	24,51	13,92	17,32	2,03	1,47	23,25	24,05	51,24	34,69	21,45	27,55	2 157	1 036	54	3 406	246

No of tested cones **28**